AMENDMENTS TO THE CLAIMS:

Please amend the claims as follows.

1. (Currently amended) A functional roll film comprising:

a transparent plastic film having gas barrier properties, and having an inorganic oxide layer on at least one surface,

wherein one roll unit of the plastic film has a width of at least 400 mm and a length of at least 4,000 m,

wherein, when from said one roll unit of the plastic film, a portion of the film having a width of at least 400 mm and a length of at least 4,000 m is cut, the <u>controlled</u> maximum thickness of the inorganic oxide layer of the portion of the film is equal to or less than 1.5 times the <u>controlled</u> minimum thickness of the inorganic oxide layer of the portion of the film among layer thickness values measured <u>along the length and the width</u> in the portion of the film.

- 2. (Previously presented) A functional roll film according to claim 1, wherein said inorganic oxide layer comprises a composite oxide having at least two components, wherein the difference between a maximum wt% and a minimum weight of one component of the composite oxide in said one roll unit of the plastic film is within 20 wt%.
- 3. (Previously presented) A functional roll film according to claim 1, wherein said one roll unit of the plastic film has a width of at least 1,000 mm and a length of at least 15,000 m.
- 4-19 (Canceled)
- 20. (Withdrawn) A process for producing a functional roll film, comprising the following steps:

providing a plastic film, having formed an inorganic oxide layer on at least one surface of the plastic film, said plastic film having transparency and gas barrier properties and being windable;

DCO 622149 2 of 7

obtaining data of the thickness of the inorganic oxide layer formed on the plastic film running in a vacuum chamber in a transverse (TD) and a longitudinal (MD) direction of the plastic film by a plurality of X-ray measuring means disposed at predetermined distances from one another in the transverse direction of the plastic film, wherein the thickness measurement by the X-ray measuring means is carried out continuously; and

controlling by a control means a heating means for heating and evaporating an evaporation material for the inorganic oxide layer based on said data of the thickness of the inorganic oxide layer, such that an evaporation rate of the evaporation material is controlled in both the transverse (TD) and the longitudinal direction (MD), so that the maximum thickness of said inorganic oxide layer is equal to or less than 1.5 times the minimum thickness, said maximum thickness being the thickness of the thickness of the thickness measured in one roll unit.

- 21. (Previously presented) A functional roll film according to claim 2, wherein said one roll unit of the plastic film has a width of at least 1,000 mm and a length of at least 15,000 m.
- 22. (Previously presented) A functional roll film according to claim 1, wherein said one roll unit of the plastic film has a width of 400 to 1,000 mm and a length of 4,000 to 10,000 m.
- 23. (New) A functional roll film comprising:

a transparent plastic film having gas barrier properties, and having an inorganic oxide layer on at least one surface,

wherein one roll unit of the plastic film has a width of at least 400 mm and a length of at least 4,000 m,

wherein, when from said one roll unit of the plastic film, a portion of the film having a width of at least 400 mm and a length of at least 4,000 m is cut, the ratio of a controlled maximum thickness of the inorganic oxide layer of the portion of the film to a

DCO 622149 3 of 7

Response to February 2, 2006 Final Office Action Appn. Serial No. 09/500,132 Atty. Docket No. 11197/1

controlled minimum thickness of the inorganic oxide layer of the portion of the film is equal to or less than 1.5 along the length and the width in the portion of the film,

wherein static electricity of said plastic film having said inorganic oxide layer is in a range from $-10 \, kV$ to $+10 \, kV$.

DCO 622149 4.of 7